

Saponification-resistant, adhesion-improving bonding course for mineral plasters on smooth, high-density substrates

Characteristics

VESTEROL® Kontakt 10D is a saponification-resistant synthetic resin dispersion containing granular fillers and adhesive additives.

The dried film creates an excellent bond even on extremely dense and smooth mineral substrates. It also provides an adhesive surface and exceptionally strong anchorage for subsequent plaster layers thanks to the cubic grains in the aggregates used.

It reduces and balances the substrate's absorbency and prevents rapid dehydration and cracking of plaster layers.

It prevents damaging ettringite formation from gypsum plaster on fresh concrete substrates and covers minor release agent residues.

- Adhesion-active
- Surface stabiliser
- Saponification-resistant
- Provides a rough substrate for plaster application

Use

VESTEROL® Kontakt 10D is used to improve the adhesion of problematic substrates for subsequent layers of gypsum, lime and cement-based plasters. For stabilising, sanding and dusting surfaces.

Areas of application:

- Outdoors and indoors
- Fresh concrete surfaces
- Very high-density and smooth precast concrete elements
- Highly absorbent substrates, building materials (aerated concrete)
- Impregnated and painted surfaces

Specifications

Packaging	PE bucket
Container size	20 kg / 5 kg
Delivery form	16 / 80 containers/pallet
Colour	red and white
Density	1.37 kg/l
Application temperature	+5 °C to +35 °C
Drying time ¹⁾	approx. 3 hours
Storage	frost-free, 12 months

Quantity required

Depending on the substrate 0.25 kg/m²

¹⁾ At +20 °C and 60 % relative atmospheric humidity.



Application

1. Depending on the absorbency of the substrate, dilute **VESTEROL® Kontakt 10D** with up to 20 % of water.
2. The product is applied with a roller or wide brush.
3. Clean all processing equipment with water immediately after use.

Post-treatment

Plaster can be applied when the **VESTEROL® Kontakt 10D** has thoroughly dried out (after approx. 3 hrs.).

Important notes

- Maintain the processing temperature at +5 °C to +35 °C.
- Plaster can be applied after **VESTEROL® Kontakt 10D** has fully dried out.
- On plaster with low binding-agent content, carry out a preliminary test.
- Not to be used in areas exposed to continuous moisture.

Ingredients

Plastic dispersion, fillers, granulates, pigments

Safety provisions/recommendations

Observe the usual hygiene procedures and precautionary measures when handling chemical products. Wear suitable work protection clothing.

Disposal

The local waste removal regulations must be observed.

Manufacturer

Heinrich Hahne GmbH & Co KG
Heinrich-Hahne-Weg 11
D-45711 Datteln