



# MULTIFIX RAPIDE



## Fast-setting ready-to-use cement

### CHARACTERISTICS

**MULTIFIX RAPIDE** is particularly useful for urgent installation, repair and sealing work.

**MULTIFIX RAPIDE** is free of chlorine or corrosion-promoting agents, and reduces bloom and discoloration.

For internal or external use.

### APPLICATIONS

- mounting work, electrical or sanitary installations.
- plugging, pointing, water leaks, damp sheets.
- miscellaneous repairs (bridges, balconies, balustrades, steps, etc...).
- sealing and anchoring.
- securing gates, piling, gantries, fences, etc. ...
- rapid fixing of cat's eyes.
- numerous prefabrication applications.

### MECHANICALS RESISTANCE

Resistance	30 minutes	1 hour	24 hours
Flexion (N/mm <sup>2</sup> )	2,38	5,48	6,2
Compression (N/mm <sup>2</sup> )	16,5	39,54	44,38



Résistance	3 days	7 days	28 days
Flexion (N/mm <sup>2</sup> )		10,83	9,02
Compression (N/mm <sup>2</sup> )		70,23	82,57



**ETS CHIMIQUES CLOQUETTE**

Av. Georges Truffaut 57  
B-4020 Liège BELGIUM

Tél. +32(0)4 362 42 61 Fax +32(0)4 362 05 24 <http://www.cloquette.be> E-mail : [cloquette@cloquette.be](mailto:cloquette@cloquette.be)

## PREPARING THE BASE MATERIAL

Any clean, resistant surface is suitable to ensure firm, solid anchoring. Remove any crumbling material or loose fragments.

Moisten the base material before application.

For application on plaster, please consult us.

## PREPARING THE PRODUCT

### Test results:

Add water to **MULTIFIX RAPIDE** in a proportion of 1:3 or 1:4, i.e. approx. ¼ litre of water to 1 kg of **MULTIFIX RAPIDE**.

Never prepare more of the product than can be applied during about 3 minutes of work. After this time, the mixture starts to set and can no longer be used.

Final setting occurs after around 10-15 minutes depending on the ambient temperature, and the temperature of the water and the base material.

## REPAIRING WATER LEAKS

For this kind of application, you are advised to use as little water as possible to make up the **MULTIFIX RAPIDE**. Apply the mortar in a plastic consistency to the site of the repair. Allow the product to warm up and wait until a sufficient degree of hardness has been obtained.

## PACKAGING UNITS

Bag of 25 kg. - palettes de 1200 kg (48 x 25 kg).

Tub of 15 kg. - palettes de 495 kg (33 x 15 kg).

Tub of 5 kg.

## STORAGE

**Multifix rapide** should be stored in a dry place, and keeps for around 6 months.

## HEALTH PROTECTION MEASURES

### Phrases R :

36/37/38 : irritant pour les yeux, les voies respiratoires et la peau.

### Phrases S :

02 : conserver hors de portée des enfants.

24/25 : éviter le contact avec la peau et les yeux.

26 : en cas de contact avec les yeux, laver immédiatement et abondamment avec de l'eau et consulter un spécialiste.

37 : porter des gants appropriés.

46 : en cas d'ingestion consulter immédiatement un médecin et lui montrer l'emballage ou l'étiquette.

Although this technical form is based on years of experiences and research we can take no responsibility for the obtained results because we can not evaluate the conditions where in you will apply the product and his components. So we strongly advice you to perform premature tests to evaluate the efficiency of the product for your application. **UPGRADE 03/2003**



SPRL

**ETS CHIMIQUES CLOQUETTE**

BVBA

Av. Georges Truffaut 57  
B-4020 Liège BELGIUM

Tél. +32(0)4 362 42 61 Fax +32(0)4 362 05 24 <http://www.cloquette.be> E-mail : [cloquette@cloquette.be](mailto:cloquette@cloquette.be)